

IN THE CLAIMS:

The pending claims are set forth below and have been amended and/or cancelled, without prejudice, where noted:

1. (Original) A film product comprising:
a metallocene catalyzed polypropylene; and
a tenacity of at least about 2.5 g/den,
wherein the film product is capable of being drawn at a draw ratio of from about 5.0:1 to about 10.0:1.
2. (Original) The film product of claim 1, wherein the film product further comprises a tenacity of about 5.0 g/den.
3. (Original) The film product of claim 2, wherein the film product is capable of being processed into at least one of a slit tape and a woven product, wherein the tenacity of the woven product is about 4.8 g/den.
4. (Original) The film product of claim 1, wherein the draw ratio is about 9.25:1.
5. (Original) The film product of claim 1, wherein the metallocene catalyzed polypropylene comprises at least one additive.
6. (Original) The film product of claim 1, wherein the film product is capable of being processed into a slit tape product.
7. (Original) The film product of claim 6, wherein at least one of the film product and the slit tape product are capable of being woven into a woven product.
8. (Original) The film product of claim 7, wherein the woven product comprises a tenacity of within about 10.0 percent of the tenacity of the at least one of the film product and the slit tape product.

9. (Original) The film product of claim 1, wherein the metallocene catalyzed polypropylene comprises a metallocene catalyzed isotactic polypropylene.
10. (Original) The film product of claim 9, wherein the metallocene catalyzed isotactic polypropylene comprises an isotacticity of less than about 99.0 percent.
11. (Original) The film product of claim 9, wherein the metallocene catalyzed isotactic polypropylene comprises an insertion error of more than about 2.0 percent.
12. (Original) The film product of claim 1, wherein the metallocene catalyzed polypropylene comprises a polymerized propylene.
13. (Original) A film product of a process comprising:
- (A) polymerizing a monomer in the presence of a metallocene catalyst system to produce metallocene catalyzed polypropylene, wherein the metallocene catalyst system comprises a metallocene catalyst;
 - (B) processing the metallocene catalyzed polypropylene into a film product; and
 - (C) drawing the film product at a draw ratio of from about 5.0:1 to about 10.0:1, the film product comprising a tenacity of at least about 2.5 g/den.
14. (Original) The film product of claim 13, wherein the monomer comprises a propylene.
15. (Original) The film product of claim 13, wherein the metallocene catalyst system comprises a co-catalyst.
16. (Original) The film product of claim 13, wherein the co-catalyst comprises an organoaluminum compound.

17. (Original) The film product of claim 13, wherein the metallocene catalyst system comprises at least one of a homogenous catalyst system and a supported catalyst system.

18. (Original) The film product of claim 13, wherein said polymerizing the monomer is performed in a loop reactor system.

19. (Original) The film product of claim 13, wherein said process further comprises

- (i) extruding the metallocene catalyzed polypropylene; and
- (ii) drawing the metallocene catalyzed polypropylene through a die.

20. (Original) The film product of claim 13, wherein said polymerizing the monomer further comprises adding at least one additive.

21. (Original) The film product of claim 13, wherein the process further comprises

- (i) processing the film product into a slit tape product, the processing comprising slitting the film product.

22. (Original) The film product of claim 21, wherein the process further comprises

- (i) weaving the slit tape product into a fabric.

23. (Original) The film product of claim 22, wherein the fabric comprises a tenacity of within about 10.0 percent of the tenacity of the film product.

24. (Original) The film product of claim 13, wherein the process further comprises

- (i) weaving the film product into a fabric.

25. (Original) The film product of claim 24, wherein the fabric comprises a tenacity of within about 10.0 percent of the tenacity of the film product.

26. (Original) The film product of claim 13, wherein the metallocene catalyzed polypropylene further comprises a metallocene catalyzed isotactic polypropylene.

27. (Original) The film product of claim 13, wherein the film product comprises an isotacticity of less than about 99.0 percent.

28-44. (Cancelled)